

# Sika<sup>®</sup> Filler-101

## Ready to use fine surface filler

Construction

|  |  |
|--|--|
| <b>Description</b>                       | Sika Filler-101 is a water-based, ready to use fine surface filler.  |
| <b>Uses</b>                              | <ul style="list-style-type: none"> <li>• Sika Filler-101 is suitable for indoor filler work on plaster boards, fabrics, old wallpapers etc.</li> <li>• Sika Filler-101 has a very smooth finish.</li> </ul>  |
| <b>Advantages</b>                        | <ul style="list-style-type: none"> <li>• Ready to use, no mixing required.</li> <li>• Easy application.</li> <li>• High initial tack or grab on plaster and concrete.</li> <li>• Quick drying.</li> </ul>  |
| <b>Storage and Shelf Life</b>            | 12 months from date of production if stored properly in undamaged and unopened original sealed packaging, in cool and dry conditions. Protect from frost.  |
| <b>Instructions for Use</b>              |  |
| <b>Surface Preparation</b>               | All surfaces must be clean, dry, free from dust and oil.   |
| <b>Mixing</b>                            | Sika Filler-101 is supplied ready to use – no mixing is required.  |
| <b>Consumption</b>                       | This depends on the substrate roughness and thickness of the layer applied. As a guide, 1 litre of Sika Filler-101 can fill 1 m <sup>2</sup> per mm thick.   |
| <b>Application</b>                       | Sika Filler-101 can be applied with spatula in layer thickness from 0 – 3 mm. When filling deeper holes or cracks the filler must be applied in several layers and must be allowed to almost dry. Holes and cracks from 4 –15 mm can more easily be filled with Sika Filler-105. When dried finish the surface with Sika Filler-101. |
| <b>Waiting Time/<br/>Overcoatability</b> | Drying Time: 2 hours<br>Paintability: 4 hours  |
| <b>Cleaning</b>                          | Clean all tools and equipment immediately after use with water. Hardened / cured material can only be removed mechanically.  |

**Technical Data (Typical)**

|                              |  |
|------------------------------|--|
| <b>Colour</b>                | White paste                                      |
| <b>Density</b>               | 1.100 kg/litre                                   |
| <b>Chemical Base</b>         | Filled styrene-acrylate dispersion               |
| <b>Solid Content</b>         | 55%  |
| <b>Grading</b>               | D <sub>max</sub> : 0.12 mm                       |
| <b>Layer Thickness</b>       | 3 mm max.  |
| <b>Substrate Temperature</b> | +5°C min. / +35°C max.                           |
| <b>Ambient Temperature</b>   | +5°C min. / +35°C max.                           |
| <b>Packaging</b>             | 500 ml plastic tube<br>5 l and 10 l plastic pail |

**Important Notification**

The information, and, in particular, the recommendations relating to the application and end-use of Sika's products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject of our terms and conditions of sale. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

PLEASE CONSULT OUR TECHNICAL DEPARTMENT FOR FURTHER INFORMATION.

# Construction

