

Sikafloor®-262 AS

2-part epoxy electrostatically conductive coating

Product

Description

Sikafloor®-262 AS is a two part, self-smoothing, coloured epoxy resin coating.

Uses

- For the production of electrostatically conductive and decorative, protective coatings on concrete or cement screeds
- Suitable as a wearing course in industries such as automotive, electronic and pharmaceutical manufacturing, storage facilities and warehouses
- Particularly suitable for areas with sensitive electronic equipment e.g. CNC machinery, computer rooms, aircraft maintenance sheds, battery-charging rooms and areas subject to high explosion risks etc.

Characteristics / Advantages

- Electrostatically conductive
- Good chemical and mechanical resistance
- Easy to clean
- Economical
- Liquid proof
- Solvent-free
- Tight, glossy surface
- Slip resistant surface possible

Approval / Standards

Conforms to the requirements of DIN IEC 61340-4-1 (Polymer Institute, P 2061-3)

Product Data

Form

Appearance / Colours

Resin - part A: coloured, liquid
Hardener - part B: transparent, liquid

For colour range refer to Sika's Technical Services department.

Due to the nature of the carbon fibers providing the conductivity, it is not possible to achieve exact colour matching. With very bright colours (such as yellow and orange), this effect is increased. Under direct sun radiation there may be some discolouration and colour deviation, this has no influence on the function and performance of the coating.

Construction



Packaging	Part A:	21 kg containers
	Part B:	4 kg containers
	Part A+B:	25 kg ready to mix units
	Bulk packaging:	
	Part A:	180 kg drums
	Part B:	180 kg drums

Storage

Storage Conditions / Shelf-Life	12 months from date of production if stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30°C.
--	--

Technical Data

Chemical Base	Epoxy	
Density	Part A:	~ 1.70 kg/l (DIN EN ISO 2811-1)
	Part B:	~ 1.03 kg/l
	Mixed resin:	~ 1.5 kg/l
	Filled resin 1 : 0.4 :	~ 1.7 kg/l
	All Density values at +23°C	
Solid Content	~ 100% (by volume) / ~ 100% (by weight)	
Electrostatic Behaviour	Resistance to earth R _E	10 ⁴ -10 ⁶ Ω (DIN IEC 61340-4-1)

Mechanical / Physical Properties

Compressive Strength	Resin: ~ 80 N/mm ² (28 days / +23°C)	(EN 196-1)
Flexural Strength	Resin: ~ 40 N/mm ² (28 days / +23°C)	(EN 196-1)
Bond Strength	> 1.5 N/mm ² (failure in concrete)	(ISO 4624)
Shore D Hardness	81 (3 days / +23°C)	(DIN 53 505)
Abrasion Resistance	65 mg (CS 10/1000/1000) (8 days / +23°C)	(DIN 53 109 (Taber Abrader Test))

Resistance

Chemical Resistance Resistant to many chemicals. Please ask for a detailed chemical resistance table.

Thermal Resistance

Exposure*	Dry heat
Permanent	+50°C
Short-term max. 7 d	+80°C
Short-term max. 12 h	+100°C

Short-term moist/wet heat* up to +80°C where exposure is only occasional (i.e. during steam cleaning etc.)

*No simultaneous chemical and mechanical exposure.

System Information

System Structure	Primer:	1 x Sikafloor®-156
	Earthing connection:	Sikafloor® Earthing Kit
	Conductive coat:	1 x Sikafloor®-220 W Conductive
	Conductive wearing course:	1 x Sikafloor®-262 AS, filled with quartz sand 0.1 - 0.3 mm

Note: This system configuration must be fully complied with as described and may not be changed.

Application Details

Consumption / Dosage

Coating System	Product	Consumption
Primer	Sikafloor® -156	0.3 - 0.5 kg/m ²
Levelling (optional)	Sikafloor® -156 mortar	Refer to PDS of Sikafloor® -156
Conductive coat	Sikafloor® -220 W Conductive	0.08 - 0.10 kg/m ²
Wearing course smooth (Film thickness ~ 1.5 mm)	Sikafloor® -262 AS filled with quartz sand 0.1 - 0.3	Maximum 2.5 kg/m ² Binder + quartz sand 10 - 15°C: 1 : 0.2 pbw (2.0 + 0.5 kg/m ²) 15 - 20°C: 1 : 0.3 pbw (1.9 + 0.6 kg/m ²) 20 - 30°C: 1 : 0.4 pbw (1.8 + 0.7 kg/m ²)
Wearing course textured (Film thickness ~ 0.5 mm)	Sikafloor® -262 AS + Extender T + Thinner C	0.75 kg/m ² 1.25 % (by weight) 2% (by weight)

These figures are theoretical and does not allow for any additional material required due to surface porosity, surface profile, variations in level and wastage etc.

Substrate Quality

The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².

The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.

If in doubt apply a test area first.

Substrate Preparation

Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve a profiled open textured surface.

Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed.

Repairs to substrate, filling of blowholes/voids and surface levelling can be carried out using appropriate products from the Sikafloor®, SikaDur® and SikaGard® range of materials.

The concrete or screed substrate has to be primed or levelled up in order to achieve an even surface. Unevenness influences the film thickness and thus the conductivity of the following layer.

High spots must be removed by e.g. grinding.

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

Application Conditions / Limitations

Substrate Temperature +10°C min. / +30°C max.

Ambient Temperature +10°C min. / +30°C max.

Substrate Humidity ≤ 4% pbw moisture content.

Test method: Sika®-Tramex meter or CM - measurement.

No rising moisture according to ASTM (Polyethylene-sheet).

Relative Air Humidity 80% r.h. max.

Dew Point Beware of condensation!

The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish.

Application Instructions

Mixing	Part A : part B = 84 : 16 (by weight)												
Mixing Time	<p>Prior to mixing stir part A mechanically. When all of part B has been added to part A, continuously mix for 2 minutes until a uniform mix has been achieved.</p> <p>When parts A and B have been mixed, the quartz sand 0.1 - 0.3 mm must be mixed with part A and B for a further 2 minutes until a uniform mix has been achieved.</p> <p>To ensure thorough mixing, pour materials into another container and mix again to achieve a consistent mix.</p> <p>Over mixing must be avoided to minimize air entrainment.</p>												
Mixing Tools	Sikafloor®-262 AS must be mechanically mixed using an electric power stirrer (300 - 400 rpm) or other suitable equipment.												
Application Method / Tools	<p>Prior to application, confirm substrate moisture content, r.h. and dew point.</p> <p>If > 4% pbw moisture content, Sikafloor® EpoCem® may be applied as a T.M.B. (temporary moisture barrier) system.</p> <p><i>Levelling:</i> Rough surfaces need to be levelled first because varying thickness of the Sikafloor®-262 AS wearing course will influence the conductivity. Therefore use Sikafloor®-156 levelling mortar (see TDS).</p> <p><i>Placing of earthing plates:</i> See below "Notes on Application / Limits".</p> <p><i>Application of Sikafloor® conductive coat:</i> See TDS of Sikafloor®-220 W conductive.</p> <p><i>Wearing course smooth:</i> Sikafloor®-262 AS is poured, spread evenly by means of a serrated trowel. Roll immediately in two directions with spiked roller to ensure even thickness.</p> <p><i>Wearing course textured:</i> Sikafloor®-262 AS is applied with a serrated trowel and then back-rolled (crosswise) with a textured roller.</p>												
Cleaning of Tools	Clean all tools and application equipment with Thinner C immediately after use. Hardened / cured material can only be mechanically removed.												
Potlife	<table border="1"><thead><tr><th>Temperatures</th><th>Time</th></tr></thead><tbody><tr><td>+10°C</td><td>~ 60 minutes</td></tr><tr><td>+20°C</td><td>~ 30 minutes</td></tr><tr><td>+30°C</td><td>~ 15 minutes</td></tr></tbody></table>	Temperatures	Time	+10°C	~ 60 minutes	+20°C	~ 30 minutes	+30°C	~ 15 minutes				
Temperatures	Time												
+10°C	~ 60 minutes												
+20°C	~ 30 minutes												
+30°C	~ 15 minutes												
Waiting Time / Overcoatability	<p>Before applying Sikafloor®-262 AS on Sikafloor®-220 W Conductive allow:</p> <table border="1"><thead><tr><th>Substrate temperature</th><th>Minimum</th><th>Maximum</th></tr></thead><tbody><tr><td>+10°C</td><td>26 hours</td><td>7 days</td></tr><tr><td>+20°C</td><td>17 hours</td><td>5 days</td></tr><tr><td>+30°C</td><td>12 hours</td><td>4 days</td></tr></tbody></table> <p>Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.</p>	Substrate temperature	Minimum	Maximum	+10°C	26 hours	7 days	+20°C	17 hours	5 days	+30°C	12 hours	4 days
Substrate temperature	Minimum	Maximum											
+10°C	26 hours	7 days											
+20°C	17 hours	5 days											
+30°C	12 hours	4 days											

Notes on Application / Limitations

This product may only be used by experienced professionals.

Do not apply Sikafloor®-262 AS on substrates in which significant vapour pressure may occur.

Do not blind the primer.

Freshly applied Sikafloor®-262 AS must be protected from damp, condensation and water for at least 24 hours.

Avoid puddles on the surface with the primer.

Only start application of Sikafloor® conductive coat after the priming coat has dried tack-free all over. Otherwise there is a risk of wrinkling or impairing of the conductive properties.

Layer thickness of wearing course: ~ 1.5 mm.

Excessive thickness (more than 2.5 kg/m²) causes reduced conductivity.

Before the application of a conductive flooring system, a reference area has to be applied. This reference area must be assessed and accepted from the contractor/client. The desired result and method of conductivity measurement must be stated in the Specification and Method Statement. The number of conductivity measurements is strongly recommended to be as shown in the table below:

Applied floor area	Number of measurements
< 10 m ²	1 measurement / m ²
10-100 m ²	10 - 20 measurements
> 100 m ²	10 measurements / 100m ²

The measuring points must have a distance of at least 50 cm to the next measuring point. In case of a measurement lower/higher than required, an additional measurement has to be carried out within 50 cm of the point with the insufficient result.

If several measuring points (R_E) of the final floor are $> 1 \cdot 10^6 \Omega$ (in case of electrostatically conductive floorings (ECF)), but the walking test ($< 100 V$, IEC 61340-4-5, IEC 61340-5-1, ESD STM 07.2-1999) and/or the system test ($< 35 M \Omega$, IEC 61340-5-1) results are within the requirements, the total area is acceptable.

Placing of earthing plates:

If the Sikafloor® Earthing Kit conductor system (system of anchored brass-plates with stable earth connection) is applied, the instructions for use have to be followed exactly. Every earthing point is able to conduct 100 m². Ensure the longest distance of each point in the area is max. 10 m to the next earthing point. Clean the earthing spots carefully. For longer distances, additional earthing plates have to be placed. If site conditions do not allow placing of additional earthing points, longer distances ($> 10 m$) have to be bridged with copper tapes. The earthing spots have to be connected to the ring-mains. This work must be executed and approved by an electrical engineer and in accordance with any relevant regulations.

Numbers of earth connections:

Per room at least 2 earthing points. The optimum number of earth connections depends on the local conditions and should be specified with documents.

The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking - reducing or breaking conductivity.

For exact colour matching, ensure the Sikafloor®-262 AS in each area is applied from the same control batch numbers.

Curing Details

Applied Product ready for use

Temperature	Foot traffic	Light traffic	Full cure
+10°C	~ 30 hours	~ 5 days	~ 10 days
+20°C	~ 24 hours	~ 3 days	~ 7 days
+30°C	~ 16 hours	~ 2 days	~ 5 days

Note: Times are approximate and will be affected by changing ambient conditions.

Cleaning / Maintenance

Methods

To maintain the appearance of the floor after application, Sikafloor®-262 AS must have all spillages removed immediately and must be regularly cleaned using a rotary brush, mechanical scrubbers, scrubber dryer, high pressure washer, wash and vacuum techniques etc. using suitable detergents and waxes.

Notes

All technical data stated in this Technical Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Handling Precautions

During application and curing in closed rooms, pits and shafts etc., adequate fresh air ventilation must be provided. Keep away from open flames including welding.

- Avoid contact with the skin, eyes and avoid breathing it's vapour.
- Wear protective gloves when mixing or using.
- If poisoning occurs, contact a doctor or Poisons Information Centre.
- If swallowed, contact a doctor or Poisons Information Centre.
- If skin contact occurs, remove contaminated clothing and wash skin thoroughly.
- If in eyes, hold eyes open, flood with water for at least 15 minutes and see a doctor.
- For more detailed information refer to our Material Safety Data Sheet.

Important Notes

Residues of material must be removed according to local regulations. Fully cured material can be disposed of as household waste under agreement with the responsible local authorities.

Detailed health and safety information as well as detailed precautionary measures e.g. physical, toxicological and ecological data can be obtained from the material safety data sheet.

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the Australian version of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

PLEASE CONSULT OUR TECHNICAL DEPARTMENT FOR FURTHER INFORMATION



Sika Australia Pty Ltd
ABN 12 001 342 329

55 Elizabeth Street
Wetherill Park NSW 2164
Tel:1300 22 33 48

www.sika.com.au

