

# Sigunit®-L75 AF

## Shotcrete admixture

**Product Description** Sigunit®-L75 AF is a high-performance liquid, alkali-free, setting and hardening accelerator for shotcrete.

**Uses** Sigunit®-L75 AF is suitable for both dry and wet spraying processes and it is used for:

- Support at the face whilst advancing tunnels and mines
- Rock- and slope stabilisation
- High quality lining shotcrete

**Characteristics / Advantages** Sigunit®-L75 AF liquid shotcrete set accelerator has the following characteristics and advantages:

- High early strength development
- Alkali-free
- Minimal strength loss of the accelerated concrete
- No pollution of groundwater by leached out alkalis
- Distinct reduction of rebound
- Improves bond of shotcrete to rock and concrete thus facilitating overhead spraying
- Distinct reduction of dust
- Chloride-free, does not negatively affect the reinforcement steel

## Product Data

### Form

**Appearance / Colour** Liquid, yellowish

**Packaging** One way drums  
Reusable plastic containers  
Bulk supply on request  
Sigunit®-L75 AF must not be stored in standard steel containers.

### Storage

**Storage Conditions / Shelf Life** 6 months from date of production if stored in original, unopened, undamaged and sealed containers, protected from direct sunlight and frost and kept at temperatures between +5°C and +40°C. Optimal storage temperature: 20°-25°C.  
After prolonged storage the performance of Sigunit®-L75 AF should be tested and the material should always be stirred up before using. Partially precipitated Sigunit®-L75 AF can be re-dissolved at temperatures of 30°-50°C. Re-dissolved material must be tested before using. Containers have to be cleaned before refilling. Containers must always be stored firmly closed.



---

**Technical Data**

---

**Chemical Base** Special inorganic materials.

---

**System Information**

---

**System Structure** The suitability of any proposed mix design must first be tested in field trials before commencement of the project.

The use of an appropriate superplasticiser (such as Sika<sup>®</sup> ViscoCrete<sup>®</sup> / SikaTard<sup>®</sup>-930) is essential.

Temperature of fresh concrete: > +15°C

---

**Application Details**

---

**Dosage** The correct dosage must be determined by preliminary testing. For layer thicknesses of up to 10 cm in one pass, dosage is between 3% and 8% of weight of binder.

Dosage of Sigunit<sup>®</sup>-L75 AF is by peristaltic pump such as the Sika<sup>®</sup> Aliva-403 pump. Optimized mixing with the concrete mix is also essential.

The following Sika<sup>®</sup> products are generally used for the basic shotcrete mix:

- Sika<sup>®</sup> ViscoCrete
- SikaTard<sup>®</sup>-930
- SikaPump<sup>®</sup>

---

**Application Instructions**

---

**Notes on Application / Limitations** If thicker layers of shotcrete are to be applied, ensure that the temperature of the basic concrete is not lower than +15°C. Lower temperatures require higher dosage of accelerator.

The substrate must be clean, free of loose stones and free of water under hydrostatic pressure.

The accelerator's effect depends on the cement content, the age and type of cement, on the substrate and the shotcrete temperature as well as on the layer thickness, spraying process, quality of equipment and application technique. The w/c ratio of the basic concrete mix in the wet spraying process, and the quantity of gauging water in the dry spraying process are also parameters influencing the acceleration effect of Sigunit<sup>®</sup>-L75 AF.

When using sulphate resistant cements strength development can be slower. Sigunit<sup>®</sup>-L75 AF is not compatible with alkaline shotcrete accelerators. Before using Sigunit<sup>®</sup>-L75 AF the accelerator hoses must be cleaned thoroughly. The use of Sigunit<sup>®</sup>-L75 AF requires technically correct dosing and conveying / spraying technology. Metal parts of the pump that come into direct contact with Sigunit<sup>®</sup>-L75 AF must be made of stainless steel.

Contact your local Sika company for any additional technical support required.

---

**Value Base**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

---

**Health and Safety Information**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

---

---

## Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika's products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject of our terms and conditions of sale. Users should always refer to the most recent issue of the Australian version of the Product Data Sheet for the product concerned, copies of which will be supplied on request.

PLEASE CONSULT OUR TECHNICAL DEPARTMENT FOR FURTHER INFORMATION.

---

